FRITZ-PAK
fritzpak.com

FILL FLOW

FLOWABLE FILL ADMIXTURE

Fritz-Pak Fill Flow produces a flowable fill. This admixture provides a better quality material, with a lower risk of bleed water. Fill Flow is environmentally safe and compatible with all conventional flowable fill mixes.

ADVANTAGES

- Increased volume of materials
- Reduced bleed water
- English & Spanish instructions
- Easy storage & transportation

MIX DESIGN

- Sand/Small Aggregate - 2200 lbs
- Water - 200 lbs
- Cement - 50-150 lbs
- Fill Flow - 1 lb

DOSAGE

Use one 1-pound (454 g) bag for 1 cubic yard of CLSM. Fill Flow will increase the material volume 20% - 35%. Allow for approximately 50% water reduction in the CLSM mix.

DIRECTIONS

1. Use one 1-lb (454 g) bag to produce 1 cubic yard of controlled low strength material.

2. Fill Flow should be added to the drum with the primary mix water.

3. Remove the outer bag. Add the inner bag to the central mixer or ready mix truck drum.

4. After all ingredients are added, the drum should be turned at mixing speed for 5-7 minutes. Improper mixing can result in poor performance.

CERTIFICATIONS

There are no applicable standards for this product.

PACKAGING

ITEM NUMBER	WEIGHT	BAGS PER CASE	CASES PER PALLET
95669	1 pound	24	30
95670	50 pounds	1	20

FRITZ-PAK
fritzpak.com

FREQUENTLY ASKED QUESTIONS

QUESTIONS	ANSWERS
What is the shelf life of Fill Flow?	If stored properly, about 3-6 years. If the material ever seems hard or caked, do not use it. It will not break up in the mix.
What kind of admixture is Fill Flow?	It is a very high strength surfactant that causes air bubbles to form in high mineral concentration solutions, such as cement pastes.
How does Fill Flow work?	It creates billions of air bubbles that serve as “ball bearings” within the flowable-fill and increase the flow properties.
What kind of unit weight can I expect?	Unit weight is dependent on mix design and size of sands. Typically you should expect a unit weight of 90-120 pounds per cubit foot.
What is the recommended addition procedure for Fill Flow?	It should be added at the job site. Fill Flow will increase the volume and flowing properties of the flowable fill. If added at the plant, the possibility of spills increase.
Will I experience a reduction in strength of the flowable fill?	No. You are increasing the air content, but you are also reducing the water content. As you reduce the water/cement ratio, the cement paste increases enough strength to compensate for the increased air content.
What standards does Fill Flow meet?	Currently there are no national standards for additives for flowable fill. Most states have specifications for the flowable fill produced.
Will I need more or less water in my flowable fill mix dosed with Fill Flow?	You will need less water. Typically you will only use 25-30 gallons of water per cubic yard of flowable fill.
Will Fill Flow reduce the strength the mix?	No. You are increasing the air content, but you are also reducing the water content. As you reduce the water/cement ratio, the cement paste increases enough strength to compensate for the increased air content.
For pumping flowable fill long distances, what do you recommend?	Besides making the flowable fill with Fill Flow we recommend adding one bag of Slick-Pak II for every 3 yards to improve pumpability.

COMPATIBILITY AND STORAGE

Fill Flow is compatible with all conventional CLSM materials. Fill Flow contains no calcium chloride or other corrosive agents. Superplasticizers, water reducers and dispersants may reduce the effectiveness of Fill Flow.

WARRANTY

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions made concerning uses or applications are only the opinion of Fritz-Pak Corporation and users should make their own tests to determine the suitability of these products for their own particular purposes. Because of numerous factors affecting results, Fritz-Pak Corporation makes no warranty of any kind, expressed or implied, including those of merchantability and fitness for purpose. Statements herein, therefore, should not be construed as representations or warranties. The responsibility of Fritz-Pak Corporation for claims arising out of breach of warranty, negligence, strict liability, or otherwise are limited to the purchase price of the materials.

© 2025 Fritz-Pak Corporation