

Gypsum Retarder

Fritz-Pak Gypsum Retarder is a dry, powdered admixture used for extending the set time of gypsum or gypsum-containing blended materials. It is an organic synthetic poly-oxy-methylene amino acid of high purity. It does not contain any carriers or extenders.

Gypsum Retarder does not contain any materials that interfere with Portland cement or Calcium Aluminate cements. It can be used in blends of gypsum with these type of cements to prevent the early stiffening caused by gypsum. Recommended for industrial use only.

MEETS STANDARDS:

There are no applicable standards for this product.

PACKAGING:

SIZE	44 lb. Bulk Bag
BAGS/CASE	1
CASES/PALLET	40

High-Strength Retarder



No 99419

BENEFITS:

- It is a high-strength retarder, effective in low doses
- It does not produce offensive odors & is non-hazardous
- Easy dosing
- Potency does not wain over-time with storage

INSTRUCTIONS

- Determine the estimated dosage required for set retardation & validate the dosage required from field trials.
- For batch blending: Add the Gypsum Retarder to each batch of gypsum and blend for approximately 5 minutes to insure proper dispersion.
- For in-line or continuous blending: It might be better to dilute the retarder to insure proper addition. Use calcium carbonate or hydrated gypsum as the filler in proportions of 9 parts filler to 1 part Gypsum Retarder for 10% active ingredient. Or use 1 part Gypsum Retarder to 99 parts filler for a 1% active ingredient.

FAQ

- Q:** Does gypsum retarder give off a strong odor?
- A:** No. Gypsum retarder does not have any odor.
- Q:** Is gypsum retarder available in our signature water-soluble bags?
- A:** No. Gypsum retarder is for industrial use, and therefore is only available in 44 lb. bags.
- Q:** Will gypsum retarder retard Portland or calcium aluminate cement?
- A:** No. Gypsum retarder is formulated specifically to retard only gypsum.
- Q:** Can gypsum retarder be used in blends of cement and gypsum?
- A:** Yes, but you may need to increase the dosage of gypsum retarder.

COMPATIBILITY

Gypsum Retarder is compatible with most concrete and cement admixtures. When using more than one admixture, each product should be dispensed separately. Gypsum Retarder does not contain calcium chloride, nitrates, or other potentially corrosive materials. Store in a dry location, protected from breakage, deterioration, and contamination. It is not subject to damage from freezing temperatures.

WARRANTY

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions made concerning uses or applications are only the opinion of Fritz-Pak Corporation and users should make their own tests to determine the suitability of these products for their own particular purposes. Because of numerous factors affecting results, Fritz-Pak Corporation makes no warranty of any kind, expressed or implied, including those of merchantability and fitness for purpose. Statements herein, therefore, should not be construed as representations or warranties. The responsibility of Fritz-Pak Corporation for claims arising out of breach of warranty, negligence, strict liability, or otherwise are limited to the purchase price of the materials.

© 2023 Fritz-Pak Corporation