

## Standard Delay Set

## Delay Set Admixture

Fritz-Pak Standard Delayed Set is a dry, powdered admixture, packaged in a ready-to-use water-soluble bag. It does not contain any calcium chloride or other potentially corrosive materials and is compatible with all standard concrete admixtures. Adding one bag to your truck will delay the set time of four yards of concrete by up to one hour. If you need additional time, you can adjust the dosage. When adding Standard Delay to your truck, it is very important to mix the truck thoroughly to prevent brown stains in the concrete.



No 95200

## MEETS STANDARDS

ASTM C-494 Type D;  
AASHTO M-194; CRD C-87

## PACKAGING:

<b>SIZE</b>	2 lb. Bags
<b>BAGS/CASE</b>	18
<b>CASES/PALLET</b>	24

Also available in 50 lb. bags.

## ADVANTAGES

- Allows for extended delivery
- Easy use & transportation
- Improved concrete finishing
- Reduced risk of cracking

## INSTRUCTIONS

Use 1 bag for every 4 yards of concrete for every hour you wish to delay the concrete.

- Add the water-soluble inner bag to the concrete truck. Recycle the outer packaging.
- Mix at high speed (15 RPM) for 5 to 7 minutes.
- Concrete will gain 2 to 6 inches in slump, and the air content may increase slightly. The concrete will return to normal specifications when set delay is complete.
- If you need to redose Standard Delay, it should be done before the concrete has returned to original slump.

## FAQ

**Q:** Will standard Delay Set affect color?

**A:** Standard Delay Set will not affect the color of gray concrete. If you are using a white cement, use our Plaster Delay Set instead.

**Q:** How do I know when setting has started?

**A:** When concrete starts to set up, you will notice an increase in both slump & concrete temperature. At this point a delay set will no longer work.

**Q:** What is the difference between Standard Delay Set & Standard Delay Set?

**A:** They are the same product. The only difference is the packaging size & dosage rates.

## DOSAGE RATES FOR STANDARD DELAY SET

TEMPERATURE	DOSE OF STANDARD DELAY / 100 LBS CEMENT	DOSE OF STANDARD DELAY / 1 KG CEMENT
< 60 °F (< 15 °C)	1.0 oz.	0.62 g.
60 - 80 °F (15 - 27 °C)	1.3 oz.	0.83 g.
> 60 °F (> 27 °C)	1.7 oz.	1.03 g.

## COMPATIBILITY

Standard Delay Set is compatible with most concrete and cement admixtures. When using more than one admixture, each product should be dispensed separately. Standard Delay Set does not contain calcium chloride, nitrates, or other potentially corrosive materials. Store in a dry location, protected from breakage, deterioration, and contamination. Standard Delay Set is not subject to damage from freezing temperatures.

## WARRANTY

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions made concerning uses or applications are only the opinion of Fritz-Pak Corporation and users should make their own tests to determine the suitability of these products for their own particular purposes. Because of numerous factors affecting results, Fritz-Pak Corporation makes no warranty of any kind, expressed or implied, including those of merchantability and fitness for purpose. Statements herein, therefore, should not be construed as representations or warranties. The responsibility of Fritz-Pak Corporation for claims arising out of breach of warranty, negligence, strict liability, or otherwise are limited to the purchase price of the materials.

© 2023 Fritz-Pak Corporation