

Supercizer 5

Premium Superplasticizer

Fritz-Pak Supercizer 5 is formulated to produce stronger more durable concrete. As a superplasticizer, Supercizer 5 may be added with the normal amount of mix water to produce more flowable concrete with up to a 6 inch slump increase. When used as a high-range water reducer, Supercizer 5 will reduce water requirements up to 25%, increase concrete compressive strength at all ages, reduce permeability, and increase durability. This product does not contain calcium chloride, nitrates, nitrites, or other potentially corrosive materials, and comes packaged in our signature **water-soluble bag** for easy use.



No 95600

MEETS STANDARDS

ASTM C-494 Type F;
AASHTO M-194; CRD C-87

PACKAGING:

SIZE	1.75 lb. Bags
BAGS/CASE	24
CASES/PALLET	25

Also available in 50 lb. bags.

ADVANTAGES

- 25% water reduction or 6 inch slump increase
- Reduced segregation in mix
- Reduced shrinkage cracks
- Increased early & ultimate concrete strengths



DOSAGE

Use a dosage rate equal to 1 to 7 ounces per 100 pounds (0.6 to 4.5 grams per kilogram) of total cementitious materials (0.06 to 0.45%). One 1.75-pound (1.1-kilogram) bag of Supercizer 5 is recommended for each cubic yard (cubic meter) of concrete to increase the slump up to 6 inches (15 centimeters) or to achieve up to 25% water reduction. The slump gain will remain in effect for 30 to 45 minutes. The concrete will then gradually return to the original slump. Concrete temperature, ambient temperature or concrete mixes containing accelerators, retarders, or special admixtures such as silica fume may require dosage rates outside the recommended range. It is recommended that testing be done to determine the suitability of Supercizer 5 to your mix designs.

DIRECTIONS

1. Determine the amount of Supercizer 5 required. See Recommended Dosage Rate.
2. Each Supercizer 5 package is double bagged. Remove the protective outer bag and add the water-soluble Fritz-Pak inner bag to the concrete mix. The entire inner bag will easily dissolve.
3. Mix at high speed for 5 to 7 minutes to insure that the Supercizer 5 is uniformly dispersed throughout the mix. Improper mixing can result in poor performance.
4. Concrete containing Supercizer 5 may be redosed if necessary.

FREQUENTLY ASKED QUESTIONS

- Q.** What is the shelf life of Supercizer 5?
- A.** If stored properly, about 1-3 years. If the material ever seems hard or caked, do not use it. It will not break up in the mix.
- Q.** Will it discolor the concrete?
- A.** No. In fact, adding Supercizer 5 before adding color will improve the mixing of color into the concrete.
- Q.** Will it change the set time?
- A.** No, it will not speed or slow the set.
- Q.** Will Supercizer 5 change the air content of my concrete?
- A.** No, at the recommended dosage rate, no change in entrained air content should occur.

Q. Will it change my concrete strength?

A. If you use less water when adding Supercizer 5, your concrete will be stronger. If your water content is not changed, strength may only improve minimally.

Q. What standards does it meet?

A. It meets ASTM C-494 type F, AASHTO M-194 and CRD C-87 standards.

Q. Do you recommend Supercizer 5 for shotcrete?

A. Yes. Supercizer 5 is the most indicated product for shotcrete applications.

COMPATIBILITY & PRECAUTIONS

Supercizer 5 is compatible with most concrete and cement admixtures. When using more than one admixture, each product should be dispensed separately. Supercizer 5 does not contain calcium chloride, nitrates, or other potentially corrosive materials. Store in a dry location, protected from breakage, deterioration, and contamination. Supercizer 5 is not subject to damage from freezing temperatures.

WARRANTY

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions made concerning uses or applications are only the opinion of Fritz-Pak Corporation and users should make their own tests to determine the suitability of these products for their own particular purposes. Because of numerous factors affecting results, Fritz-Pak Corporation makes no warranty of any kind, expressed or implied, including those of merchantability and fitness for purpose. Statements herein, therefore, should not be construed as representations or warranties. The responsibility of Fritz-Pak Corporation for claims arising out of breach of warranty, negligence, strict liability, or otherwise are limited to the purchase price of the materials.

© 2023 Fritz-Pak Corporation